



TECHNICAL DATA SHEET – KCF3KPL224

Kordsa Textile Reinforcements for Composite Industry

Kordsa has a wide range of unidirectional and bidirectional fabrics (plain, twill, harness satin and basket). Carbon, glass and aramid fibers can be used as reinforcement materials in traditional and hybrid fabrics.

Applications: Prepreg production, RTM, vacuum infusion, wet lay-up, preforming

DESCRIPTION

Type of yarns	Warp: MRC CF PYROFIL HT 3000 TR30S 3L
	Weft: MRC CF PYROFIL HT 3000 TR30S 3L
Nominal weight	224 g/m ² ± 3%
Weave style	Plain
Width	1255 mm +/- 10/0 mm
Core diameter	152 mm

CHARACTERISTICS

Construction	Warp: 5,6 yarn/cm
	Weft: 5,6 picks/cm
Weight distribution	Warp: 50%
	Weft: 50%

KORDSA
TEKNIK TEKSTIL A.Ş.

CENTER:
ALKAHYA FATİH MAH.
SANAYİCİ CAD. NO:90
41310 İZMİT, KOCAELİ
T 0282 318 70 00
F 0282 318 70 70
www.kordsa.com
Mersis No: 0577-0053-5640-0013
Trade Registry Office: Kocaeli
Trade Registry No: 28907

TEKNOPARK OFFICE:
SANAYİ MAH. TEKNOPARK BULVARI
NO.1/1B 34906 PENDİK, İSTANBUL
T 0216 300 10 00

BRAZIL
CHINA (Contact Office)
EGYPT
INDONESIA
USA
THAILAND
TURKEY



www.kordsaglobal.com
reinforcer@kordsaglobal.com

NOTICE –All rights reserved. Kordsa reserves the right to update, revise or modify such technical data and information at any time. The data disclosed herein is for information purposes only without any legal responsibility attributable to Kordsa. Kordsa recommends Customer’s own testing of the suitability of our products for its particular purpose. Kordsa makes no express or implied warranty or representation, including but not limited to the warranties of merchantability, commercial availability and/or fitness for a particular purpose.